



**Europäisches
Patentamt**

**European
Patent Office**

**Office européen
des brevets**

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02079638.9

**CERTIFIED COPY OF
PRIORITY DOCUMENT**

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

THIS PAGE BLANK (USPTO)

THIS PAGE BLANK (USPTO)



Anmeldung Nr:
Application no.: 02079638.9
Demande no:

Anmeldetag:
Date of filing: 24.10.02
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

KRATON Polymers Research B.V.
Badhuisweg 3
1031 CM Amsterdam
PAYS-BAS

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se referer à la description.)

Blockcopolymer compositions, having improved mechanical properties and
processability and styrenic blockcopolymer to be used in them

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

D01F/

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR

()

BLOCKCOPOLYMER COMPOSITIONS, HAVING IMPROVED MECHANICAL
PROPERTIES AND PROCESSABILITY AND STYRENIC BLOCKCOPOLYMER
TO BE USED IN THEM.

Field of the invention

The invention relates to blockcopolymer compositions with improved mechanical properties and processability and to modified styrenic blockcopolymer to be used in them.

In particular, the invention relates to compositions comprising a modified hydrogenated styrene butadiene blockcopolymer, to be used for the manufacture of fibers, filaments, melt blown or spun bond non-wovens or cast or blown films.

Background of the Invention

Elastomeric compounds which can be easily extruded, spunbond or melt blown into elastic fibers or films having low stress relaxation, low hysteresis or permanent set, and high recoverable energy are described in United States Patents Nos. 4,663,220, 4,789,699, 4,970,259, 5,093,422, 5,705,55 6 and many others. The elastomeric fibers or films are useful in making a variety of applications such as diaper waistbands and non-woven fabrics.

Polystyrene-poly(ethylene-butylene)-polystyrene elastomeric block copolymers have been compounded with other materials such as, for example, polyolefins and tackifying resins to form extrudable elastomeric compositions which can be more easily extruded into elastic fibers or films having improved processing and/or bonding properties. Processes for making cast extruded films, extrusion blown films, extruded fibers, filaments, non-wovens and such like have high requirements around

viscosity of the compound. At the same time, applications of these extrudates in personal hygiene, food wrapping and the like result in stringent requirements on mechanical behavior; a combination of stiffness (high modulus), and excellent elasticity (good stress-relaxation and low hysteresis and permanent set) is needed. One of the greatest challenges in this field is to find a good balance between flow/viscosity and the mechanical properties mentioned above.

It is an object of the present invention to provide compositions that have excellent balance of properties in personal hygiene applications (fibers, filaments, non-wovens or cast or blown films).

Summary of the invention

Accordingly a composition is provided, which can be used for the manufacture of fibers, filaments, melt blown or spun bond non-wovens or cast or blown films, comprising at least 50 wt% of a styrenic block copolymer having a molecular structure according to the general formulae

S - EB


- S (1) or (S - EB)_n X (2), wherein each S independently is a polymer block of predominantly styrene and EB is a hydrogenated polymer block of predominantly butadiene, n is an integer equal to or greater than 2, and X is the residue of a coupling agent, having a poly(styrene) content in the range of from 10 to 29% by weight (wt%), preferably from 17 to 24 wt%, having poly(styrene) blocks (S) of an apparent molecular weight in the range of from 6,000 to 9,000 and preferably from 7,000 to 8,500, having an apparent molecular weight of the complete block copolymer in the range of from 80,000 to 150,000, having an 1,2 addition degree (vinyl content) in the precursor of the poly (butadiene) block (EB) in the range of from 60 to 80% (mole/mole), wherein the block EB has a hydrogenation degree of at least 80 % and

preferably at least 90%, and wherein diblock S-EB optionally occurs in a content of at most 20 mole% and preferably at most 10 mole%; a polyolefin in an amount of from 10 to 30 wt%; a resin which is compatible with the poly(styrene) blocks in an amount of at least 5 wt%, and a resin which is compatible with the hydrogenated polybutadiene blocks in an amount of at least 3 wt%, wherein all weight percentages are relative to the weight of the complete composition.

In addition modified styrenic block copolymers are provided which have been found to be in particular suitable in the compositions for the manufacture of fibers, filaments and melt blown or spun bond non-wovens or cast or blown films. Said products are applied for personal hygiene applications.

Accordingly styrenic block copolymers are provided to be used in compositions for the manufacture of fibers, filaments, melt blown or spun bond non-wovens, wherein

- i. the poly(styrene) content (PSC) is from 17 to 24 wt%,
- ii. the styrenic block copolymer has a molecular structure according to the general formulae



wherein each S independently is a polymer block of styrene and EB is a hydrogenated polymer block of butadiene, n is an integer equal to or greater than 2, and X is the residue of a coupling agent,

- iii. the apparent molecular weight of the poly(styrene) blocks (S) is in the range of from 7,000 to 8,500,

- iv. the apparent molecular weight of the complete styrenic block copolymer is in the range of from 80,000 to 150,000,

- v. the 1,2 addition degree (vinyl content) in the precursor poly (butadiene) block (EB) precursor is in the range of from 60 to 80 (mole/mole),

- vi. the block EB has a hydrogenation degree of at least 80% and preferably of at least 90%, and
- vii. an optional diblock S-EB content of at most 20 mole% and preferably of at most 10 mole%, relative to the total block copolymer amount.

Detailed description of the invention

Compositions according to the present invention comprise at least 50 wt% of at least one block copolymer, derived from predominantly styrene and predominantly butadiene.

Preferably said compositions comprise said block copolymer(s) in weight proportions of from 50 to 70 wt% and more preferably from 55 to 65 wt%.

Said compositions comprise in addition to the block copolymer a polyolefin in a weight proportion of from 10 to 30 wt% and preferably of from 15 to 20 wt%; a polystyrene block compatible resin in a weight proportion of at least 5 wt% and preferably of from 5 to 15 wt% and more preferably from 8 to 12 wt%; and at least 3 wt% of a hydrogenated polybutadiene compatible resin, preferably of from 3 to 10 wt% and more preferably of from 5 to 10 wt%, relative to the weight of the total composition.

With the terms "predominantly styrene" and "predominantly butadiene" respectively, as used throughout the specification, are meant that for the respective blocks to be prepared, substantially pure styrene or mixtures comprising at least 95 wt% of styrene and minor amounts of other comonomers can be used, and substantially pure butadiene or mixtures comprising at least 95 wt% of butadiene and minor amounts of other comonomers, can be used.

The small proportions of other comonomers in the polystyrene blocks can consist of structurally related comonomers such as alpha-methyl styrene, p-methyl


styrene, o-methyl styrene, p-test.butyl styrene, dimethyl styrene and vinyl naphthalene, or butadiene.

The small proportions of other comonomers in the poly(butadiene) block can consist of isoprene or styrene.

5 However, preferred block copolymers to be applied according to the present invention, contain blocks of substantially pure styrene and substantially pure butadiene.

10 The block copolymer according to the present invention may be branched or linear and may be a triblock, tetrablock or multiblock.

It has a structure represented by the following general formulae



15 wherein each S independently is a polymer block predominantly styrene, and EB is a hydrogenated polymer block of predominantly butadiene, having a hydrogenation degree of at least 80%, preferably at least 90% and more preferably more than 95%, wherein n is an integer equal to or greater than 2 and wherein X is the residue of a
20 coupling agent.

The polymer blocks S have an apparent molecular weight in the range of from 6,000 to 9,000 and preferably from 7,000 to 8,500.

25 In the block copolymers according to the present invention, the PSC is in the range of 10-29 %w, preferably 17-24 %w based on the total block copolymer. The 1,2 addition (vinyl content) in the midblock precursor is in the range of 60 to 80%, preferably in the
30 range of 65 to 75%.

The complete block copolymers according to the present invention each preferably have a total apparent molecular weight (M_w , determined by Gel Permeation Chromatography and expressed in terms of polystyrene)
35 ranging from 80,000 to 150,000, preferably from 100,000

to 120,000 (using the method described by J.R. Runyon et al in J. Polym. Sci., 13, 2359 (1969)).

The block copolymers according to the present invention can be made e.g. by coupling living diblock copolymer prepared by anionic polymerization with a coupling agent or by sequential polymerization. The latter is preferred.

It will be appreciated that block copolymers, prepared by means of coupling of living diblock copolymers by means of a coupling agent and termination of remaining living block copolymers, will finally contain small amounts (i.e. less than 20 mole% and preferably less than 10 mole%) of diblock copolymer, having the same S blocks (mole% relative to the weight of the total block copolymer).

Preferred block copolymers to be used in the compositions of the present invention do not contain any detectable amount of diblock copolymer.

As examples of the coupling agent may be mentioned tin coupling agents such as tin dichloride, monomethyltin dichloride, dimethyltin dichloride, monoethyltin dichloride, diethyltin dichloride, methyltin trichloride, monobutyltin dichloride, dibutyltin dibromide, monohexyltin dichloride and tin tetrachloride; halogenated silicon coupling agents such as dichlorosilane, monomethyldichlorosilane, dimethyldichlorosilane, diethyldichlorosilane, monobutyldichlorosilane, dibutyldichlorosilane, monohexyldichlorosilane, dihexyldichlorosilane, dibromosilane, monomethyldibromosilane, dimethyldibromosilane, silicon tetrachloride and silicon tetrabromide; alkoxysilanes such as tetramethoxysilane; divinyl aromatic compounds such as divinylbenzene en divinyl naphthalene; halogenated alkanes such as dichloroethane, dibromoethane, methylene chloride

dibromomethane, dichloropropane, dibromopropane, chloroform, trichloroethane, trichloropropane and tribromopropane; halogenated aromatic compounds such as dibromobenzene; epoxy compounds such as the diglycidyl ether of bisphenol-A (e.g. EPON 825, a trademark), and other coupling agents such as benzoic esters, CO₂, 2-chloroprene and 1 chloro-1,3-butadiene. Of these EPON 825, dibromobenzene, tetramethoxysilane and dimethyldichlorosilane are preferred.

The anionic polymerization of the conjugated diene hydrocarbons is typically controlled with structure modifiers such as diethyl ether or ethyl glyme (1,2-diethoxyethane), to obtain the desired amount of 1,2-addition. As described in Re 27,145 which is incorporated by reference herein, the level of 1,2-addition of a butadiene polymer or copolymer can greatly affect elastomeric properties after hydrogenation. The 1,2-addition of butadiene polymers significantly and surprisingly additionally influences the polymer as described above. More in particular, a 1,2-addition of 78% (within the scope of this invention) is achieved during polymerization by the presence of about 300 ppm of 1,2-diethoxypropane (DEP) in the final solution.

In general, the polymers useful in this invention may be prepared by contacting the monomer or monomers with an organoalkali metal compound in a suitable solvent at a temperature within the range from -150°C to 300°C, preferably at a temperature within the range from 0°C to 100°C. Particularly effective polymerization initiators are organolithium compounds having the general formula



wherein R is an aliphatic, cycloaliphatic, alkyl-substituted cycloaliphatic, aromatic or alkyl-substituted aromatic hydrocarbon radical having from 1 to 20 carbon atoms of which sec.butyl is preferred.

Suitable solvents include those useful in the solution polymerization of the polymer and include aliphatic, cycloaliphatic, alkyl-substituted cycloaliphatic, aromatic and alkyl-substituted aromatic hydrocarbons, ethers and mixtures thereof. Suitable solvents, then, include aliphatic hydrocarbons such as butane, pentane, hexane and heptane, cycloaliphatic hydrocarbons such as cyclopentane, cyclohexane and cycloheptane, alkyl-substituted cycloaliphatic hydrocarbons such as methylcyclohexane and methylcycloheptane, aromatic hydrocarbons such as benzene and the alkyl-substituted hydrocarbons such as toluene and xylene, and ethers such as tetrahydrofuran, diethylether and di-n-butyl ether. Preferred solvents are cyclopentane or cyclohexane.

It will be appreciated that the EB blocks in the finally applied block copolymers preferably have been selectively hydrogenated to a degree of at least 95%, whereas the poly(styrene) blocks have not been hydrogenated or only in a degree of at most 5%.

The hydrogenation of these polymers may be carried out by a variety of well established processes including hydrogenation in the presence of such catalysts as Raney Nickel, noble metals such as platinum and palladium and soluble transition metal catalysts. Suitable hydrogenation processes which can be used are ones wherein the diene-containing polymer or copolymer is dissolved in an inert hydrocarbon diluent such as cyclohexane and hydrogenated by reaction with hydrogen in the presence of a soluble hydrogenation catalyst. Such processes are disclosed in US Patent Nos. 3,113,986, 4,226,952 and Reissues 27,145, the disclosure of which are herein incorporated by reference. The polymers are hydrogenated in such a manner as to produce hydrogenated polymers having a residual unsaturation content in

polydiene blocks of less than 5 percent by weight, preferably less than 1%wt and more preferably as close to 0 percent as possible, of their original unsaturation content prior to hydrogenation. A titanium catalyst such as disclosed in US Patent 5,039,755, which is herein incorporated by reference, may also be used in the hydrogenation process.

The finally applied selectively hydrogenated block copolymers can also consist of mixtures of linear block copolymers or of mixtures of linear block copolymer and branched block copolymers.

The polyolefin used in the compositions of the present invention is preferably polypropylene (PP) or polyethylene (PE), more preferably a high MFR PP (i.e., having a melt flow rate as determined at 230 °C/2.16 kg, in accordance to ASTM D1238-95 of greater than 400 gr/10 min.). Suitable polyolefins having an MFR of about 800 gr/10 min are "VALTEC" HH442 or "MOPLIN" HF568 by Basell (trademarks), "BORFLOW" HL508 by Borealis and "MIRAE POL PA189V" by PolyMirae (trademarks). The polyolefin is preferably used in an amount of from 15 to 25 %w (on the total compound).

The polystyrene block compatible resin may be selected from the group consisting of coumarone-indene resin, polyindene resin, poly(methyl indene) resin, polystyrene resin, vinyltoluene-alpha-methylstyrene resin, alpha-methylstyrene resin and polyphenylene ether, in particular poly(2,6-dimethyl-1,4-phenylene ether). Such resins are e.g. sold under the trademarks "HERCURES", "ENDEX", "KRISTALLEX", "NEVCHEM" and "PICCOTEX". A very suitable resin is "KRISTALLEX" F-100. The compound preferably comprises from 8 to 12 %w of the polystyrene block compatible resin.

Resins compatible with the hydrogenated polybutadiene (mid)block may be selected from the group consisting of

compatible C₅ hydrocarbon resins, hydrogenated C₅ hydrocarbon resins, styrenated C₅ resins, C₅/C₉ resins, styrenated terpene resins, fully hydrogenated or partially hydrogenated C₉ hydrocarbon resins, rosins esters, rosins derivatives and mixtures thereof. These resins are e.g. sold under the trademarks "REGALITE", "REGALREZ", "ESCOREZ" and "ARKON". A very suitable resin is "REGALITE" R-1125. The compound preferably comprises from 5 to 10 %w of the (mid)block compatible resin.

It will be appreciated that another aspect of the present invention is formed by the fibers, filaments, melt blown or spun bond non-wovens or cast or blown films, obtained by processing the hereinbefore defined compositions.

A further aspect of the present invention is formed by the specific block copolymers to be used in the compositions for the manufacture of fibers, filaments, melt blown or spun bond non-wovens or cast or blown films.

The compositions of the embodiments may contain a plasticizer. However, as plasticizers have the tendency to migrate, their presence is typically to be avoided.

Other ingredients may be incorporated into the compositions according to the present invention. For instance, processing aids can be added or colorants, as well as antioxidants and other stabilizing ingredients to protect the compounds from degradation induced by heat, light and processing or during storage.

Preparation of the composition

No particular limitation is imposed on the preparation process of the compound of the present invention. Therefore, there may be used any process such as a mechanically mixing process: e.g., a Banbury mixer or a twin-screw extruder provided with adequate mixing

elements, thereby obtaining an intimate mixture of the ingredients.

Use of the composition

Compositions according to the present invention may be applied, e.g. by extrusion, for the preparation of fibers, filaments and melt blown or spun bond non-wovens or cast or blown films.

The present invention will hereinafter be described more specifically by reference to the following examples and comparative examples. However, this invention is not limited to these examples only. Incidentally, all designations of "part" or "parts" and "%" as will be used in the following examples mean part or parts by weight and percentage by weight unless expressly noted. The measurements of physical properties were conducted in accordance with the following methods.

Test methods

- melt flow rate (MFR): ASTM D1238-95 (230°C, 2.16kg)
- tensile properties on fibers:
- hysteresis: strands produced by melt index tester are clamped in a mechanical tester (Zwick). Strands are elongated to 150% extension at a speed of 100 mm/sec (load step), and immediately relaxed to zero force (unload step). A second cycle follows right after the first one. Forces at 50 and 100% elongation are recorded for the first cycle. Hysteresis is measured as the difference in energy between the load and the unload step. Permanent set is measured as the difference between the original sample length of the first cycle (force equals zero) and the sample length before the second cycle (force equals zero).
- stress-relaxation: strands produced by melt index tester are clamped in a mechanical tester (Zwick). Strands are elongated to 50% extension, in a hot-air

oven at 40°C. The samples are held in that position for 2 hrs. The force decay is measured. The stress-relaxation is expressed as the ratio between the final force and the initial force (equaling the percentage of retained stress).

- tensile properties according to ASTM D882-81 (tested on films)

Table 1 (ingredients)

Styrenic Block copolymers:	
SBC A comp.	A linear SEBS having a diblock content of about 30%; a PSC of 13.3 %, a MW (PS) of about 5,300; an apparent MW of about 145,000 and a vinyl content of 45 %
SBC B	A linear SEBS having a PSC of 21 %, a MW (PS) of about 8,000; an apparent MW of about 115,000 and a vinyl content of 65 %
SBC C comp.	A linear SEBS having a PSC of 20.5 %, a MW (PS) of about 10,000; an apparent MW of about 150,000 and a vinyl content of 68 %
SBC D comp	A linear SEBS having a PSC of 30 %, a MW (PS) of about 7,000; an apparent MW of about 80,000 and a vinyl content of 40 %
Polyolefins:	
HF568X	"VALTEC" HH442H or "MOPLIN" HF568X, a PP having an MFR of 800 g/10 min and a Modulus of 1500 MPa
PA189V	"MiraePol" PA189V, a PP having an MRF of 900 g/10 min
Endblock compatible resins:	
F-100	"KRISTALLEX" F-100; an alpha-methylstyrene resin
Midblock compatible resins	
R-1125	"REGALITE" R-1125; a fully hydrogenated C9 hydrocarbon resin

EXAMPLES 1 - 6

Compositions for the preparation of fibers, non-wovens use were prepared on a 25mm Werner & Pfleiderer ZSK25 co-rotating twin-screw extruder with 49 L/D. The ingredients from Table 1 were pre-blended according to the amounts in Table 2 in a Papenmeier internal mixer, and fed into one feeding port. Strands were cooled in a water-bath and granulated using a strand-cutter.

Strands were prepared with a Gottfert melt index tester as described in ASTM D-1238-95. The mechanical properties of these strands were measured, and the results are included in Table 2.

Table 2 composition

Examples	1	2	3	4	5	6
SBC A comp						65
SBC B	60	65	65			
SBC C comp					65	
SBC D comp				65		
HF568x	20	15	20	20	20	20
F-100	10	10	10	10	10	10
R-1125	10	10	5	5	5	5
<u>Properties</u>						
MFR (g/10 min)	49	37	30	27	11	1.5
Stress Relaxation (%)	n.m	42	40	38	41	56
Permanent Set (%)	17	12	14	24	23	11
Modulus 50%	3.17	2.32	3.18	2.64	4.31	2.16

Conclusion:

5 The compound of Example 3 is based on the right polymer at the right amount. Accordingly, it has the right balance of properties. On the other hand, the compound of Example 1 has a very high MFR and a high modulus, but a permanent set that is too high. The compound of Example 2 has a good MFR and elasticity (stress-relaxation and permanent set), but a high flow and a too low modulus.

10 In Example 4 the composition has a good flow, but a too low modulus and no elasticity (bad hysteresis and stress-relaxation).

15 In Example 5 the composition has a very high modulus, a too low flow, and no elasticity (bad hysteresis; the stress-relaxation is acceptable).

 In Example 6, the composition shows a very good elasticity (hysteresis and stress-relaxation) but a too low modulus and a very poor flow.



C L A I M S

1. A composition to be used for the manufacture of fibers, filaments, melt blown or spun bond non-wovens or cast or blown films, comprising at least 50 wt% of a styrenic block copolymer, having a molecular structure according to the general formulae

5 S - EB - S (1) or (S - EB)_n X (2), wherein
each S independently is a polymer block of predominantly styrene and EB is a hydrogenated polymer block of predominantly butadiene, n is an integer equal to or
10 greater than 2, and X is the residue of a coupling agent, having a poly(styrene) content in the range of from 10 to 29% by weight (wt%), preferably from 17 to 24 wt%, having poly(styrene) blocks (S) of an apparent molecular weight in the range of from 6,000 to 9,000 and preferably from
15 7,000 to 8,500, having an apparent molecular weight of the complete block copolymer in the range of from 80,000 to 150,000, having an 1,2-addition degree (vinyl content) in the precursor of the poly (butadiene) block (EB) in the range of from 60 to 80% (mole/mole), wherein the
20 block EB has a hydrogenation degree of at least 80 % and preferably at least 90%, and wherein diblock S-EB optionally occurs in a content of at most 20 mole% and preferably at most 10 mole%; a polyolefin in an amount of from 10 to 30 wt%; a resin which is compatible with the
25 poly(styrene) blocks in an amount of at least 5 wt%, and a resin which is compatible with the hydrogenated polybutadiene blocks in an amount of at least 3 wt%, wherein all weight percentages are relative to the weight of the complete composition.

30 2. A composition according to claim 1, wherein the polyolefin is a polypropylene having a melt flow rate greater than 400 gr/10 min (according to ASTM D1238-95).

3. Composition according to any one of claims 1 or 2, wherein the block EB of the block copolymer has a hydrogenation degree of at least 95%.


5 4. Composition according to any one of claims 1 to 3 wherein the EB block precursor has an 1,2-addition degree (vinyl content) in the range of from 65 to 75%.

5. Composition according to any one of claims 1 to 4, wherein any S-EB diblock occurs in a content of at most 10 mole%, relative to the total block copolymer amount.

10 6. Fibers, filaments, melt blown or spun bond non-wovens or cast or blown films, derived from a composition according to any one of claims 1 to 5.

7. A styrenic block copolymer, wherein

15 i. the poly(styrene) content (PSC) is from 17 to 24 wt%,
ii. the styrenic block copolymer has a molecular structure according to the general formulae



20 wherein each S independently is a polymer block of styrene and EB is a hydrogenated polymer block of butadiene, n is an integer equal to or greater than 2, and X is the residue of a coupling agent,

iii. the apparent molecular weight of the poly(styrene) blocks (S) is in the range of from 7,000 to 8,500,

25 iv. the apparent molecular weight of the complete styrenic block copolymer is in the range of from 80,000 to 150,000,

v. the 1.2 addition degree (vinyl content) in the precursor poly (butadiene) block (EB) precursor is in the
30 range of from 60 to 80 (mole/mole),

vi. the block EB has a hydrogenation degree of at least 80% and preferably of at least 90%, and

35 vii. an optional diblock S-EB content of at most 20 mole% and preferably of at most 10 mole%, relative to the total block copolymer amount.

8. A styrenic block copolymer according to claim 7 wherein the hydrogenation degree of the EB block is at least 95%.
- 5 9. A styrenic block copolymer according to claim 7 wherein the 1,2-addition degree in the EB block is in the range of from 65 to 75%.
- 10 10. A styrenic block copolymer according to any one of claims 7 to 9 wherein the apparent molecular weight of the styrenic block copolymer is in the range from 100,000 to 120.000.

THIS PAGE BLANK (USPTO)

THIS PAGE BLANK (USPTO)

A B S T R A C T

BLOCKCOPOLYMER COMPOSITIONS, HAVING IMPROVED MECHANICAL PROPERTIES AND PROCESSABILITY AND STYRENIC BLOCKCOPOLYMER TO BE USED IN THEM.

A composition to be used for the manufacture of fibers, filaments, melt blown or spun bond non-wovens or cast or blown films, comprising at least 50 wt% of a styrenic block copolymer; a polyolefin in an amount of from 10 to 30 wt%; a resin which is compatible with the poly(styrene) blocks in the styrenic block copolymer in an amount of at least 5 wt%, and a resin which is compatible with the hydrogenated polybutadiene blocks in the styrenic block copolymer an amount of at least 3 wt%, wherein all weight percentages are relative to the weight of the complete composition; styrenic block copolymers to be used therein; and fibers, melt blown or spun bond non-wovens or cast or blown films prepared from it.

THIS PAGE BLANK (USPTO)

THIS PAGE BLANK (USPTO)